



Härtevergleichstabelle

HV	HB	Shore		HRC
		D	C	
300	300	45	45	30
310	310	46	46	32
320	320	47	47	33
330	330	48	48	34
340	340	50	50	35
350	350	51	51	36
360	359	52	52	37
370	368	53	53	38
380	378	54	54	39
390	386	55	55	40
400	393	57	57	41
410	400	58	58	42
420	408	59	59	42
430	416	60	60	43
440	422	61	61	44
450	430	62	62	45
460	436	63	63	46
470	442	65	65	46
480	452	66	66	47
490	460	67	67	48
500	470	68	68	48
510	479	69	69	49
520	488	70	69	50
530	498	71	70	50
540	507	72	71	51
550	517	73	72	52
560	525	75	73	52
570	535	76	74	53
580	544	77	75	53
590	554	78	76	54
600	564	79	77	54
610	573	80	78	55
620	582	81	79	55
630	591	82	79	56
640	600	83	80	56
650	610	84	81	57
660	620	85	82	58
670	629	87	83	58
680	638	88	84	58
690	–	89	84	59
700	–	90	85	59
710	–	91	86	60
720	–	92	87	60
730	–	93	88	61
740	–	94	89	61
750	–	95	90	62
760	–	95	90	62
770	–	96	91	62
780	–	97	92	63
790	–	98	92	63
800	–	99	93	64